



CUPA 98

*Non-carbonated slate formed by tectonic compression.
Dark grey slate with thin laminations and a riven surface.*





Quarry Rande, Ortigueira (A Coruña), Spain.



Operating since 1969.



Sizes: 25x25 - 70x50 cm
Thickness: 5 - 6 - 7.5 - 9 mm



Formats



Rectangular



Rhomboid



Bullnose



Ogival



Irregular

Selections

R

H

NATURAL

Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO ₂ EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
0,12% Code: W1 (< 0,6%)	0,24% Complies (< 1,5%)	Longitudinal 58 MPA Transverse 39 MPA	S1	T1	Fullfil < 0,6%

International certifications



European Standard: EN 12326 | American Standard: ASTM C406-15