



CUPA 14

*Non-carbonated **slate** formed by tectonic compression.
Dark grey slate with thin laminations and a **riven surface**.*




Quarry Las Fuentes. Benuza (León)
Spain.



Operating since 1985.



Sizes: 20x20 - 60x45 cm
Thickness: 5 - 6,5 - 7,5 - 9 mm



Formats



Square



Rectangular



Rhomboid



Bullnose



90° Sawn

Selections

R EXCELLENCE

H

NATURAL

Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO ₂ EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
0,21% Code: W1 (< 0,4%)	0,27% Fullfil (< 2%)	Longitudinal 37 MPA	S1	T1	Fullfil < 0,4%

International certifications



European Standard: EN 12326 | British Standard: BS 680 Part 2