



CUPA 7

Non-carbonated **slate** formed by tectonic compression.
Black slate with thin laminations and a **smooth surface**.





Quarry Arcas Prada. San Pedro de Tro- nes (Leon) Spain.



Operating since 1968.



Main sizes: 16"x8" and 16"x10"
Thickness: 3/16" to 3/8"



Formats



Rectangular

Selections

EXCELLENCE

ARDOISIER

HEAVY

Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO ₂ EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
< 0,4% Code : W1 (< 0,6%)	≤ 0,2% Fullfil (< 2%)	Longitudinal ≥ 55 MPA	S1	T1	Fullfil < 0,6%

International certifications



European Standard: EN 12326 | French Specifications: NFO2/05 - N°5277 | Belgian Specifications: ATG/H876 | British Standard: BS 680 Part 2