



CUPA 13

*Non-carbonated slate formed by tectonic compression.
Blue-black slate with thin laminations and smooth surface.*





Quarry Raniella. Benuza (Leon) Spain.



Operating since 1992.



Sizes: 25x15 - 50x38 cm
Thickness: 3.75 - 5 - 7.5 - 9 - 22 mm




Formats



Rectangular Bullnose Rhomboid Ogival Innova

Selections



Technical specifications

| ABSORPTION | CARBONATE NON CARBONATED | MOR CHARACTERISTIC | SO ₂ EXPOSURE TEST | THERMAL CYCLE TEST | FREEZE THAW TEST |
|-------------------------|--------------------------|--|-------------------------------|--------------------|------------------|
| 0,22% Code: W1 (< 0,4%) | 0,47% Complies (< 1,5%) | Longitudinal 53,3 MPA Transverse 38,2 MPA | S1 | T1 | Fullfil < 0,6% |

International certifications



European Standard: EN 12326 | French Specifications: NF 02/07 N° 5279 | Belgian Specifications: ATG H695