




CUPA 14

*Non-carbonated **slate** formed by tectonic compression.
Dark grey slate with thin laminations and a **riven surface**.*






Quarry Las Fuentes. Benuza (León)
Spain.



Operating since 1985.



Sizes: 20x20 - 60x45 cm
Thickness: 5 - 6,5 - 7,5 - 9 mm



Formats



Square Rectangular Rhomboid Bullnose 90° Sawn

Selections



Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO ₂ EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
< 0,4% Code : W1 (< 0,4%)	≤ 0,2% Fullfil (< 2%)	Longitudinal ≥ 37 MPA	S1	T1	Fullfil < 0,4%

International certifications



European Standard: EN 12326 | British Standard: BS 680 Part 2