




CUPA 14

*Non-carbonated slate formed by tectonic compression.
Dark grey slate with thin laminations and a riven surface.*





Quarry Las Fuentes. Benuza (León)
Spain.



Operating since 1985.



Main sizes: 8"x6" to 24"x12"
Thickness: 3/16" to 3/8"



Formats



Rectangular

Selections

EXCELLENCE

ARDOISIER

HEAVY

Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO ₂ EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
0,21% Code : W1 (< 0,6%)	Complies (< 1,5%)	Longitudinal 43,5 MPA Transverse 45,7 MPA	S1	T1	Fulfill < 0,6%

International certifications



European Standard: EN 12326 | American Standard: ASTM C406-15