




CUPA 5


Non-carbonated **slate** formed by tectonic compression.
Dark grey slate with a **riven** surface.



 Quarry Valdacal. Puzmazán (Ourense) Spain.

 Operating since 1971.

 Sizes: 20x20 - 60x45 cm
Thickness: 5 - 6.5 - 7.5 - 9 mm



Formats



Selections



Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO ₂ EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
< 0,4% Code : W1 (< 0,6%)	≤ 0,2% Fullfil (< 2%)	Longitudinal ≥ 45 MPA	S1	T1	Fullfil < 0,6%

International certifications



European Standard: EN 12326 | French Specifications: NFO2/03 - N°5275 | Belgian Specifications: ATG/H848 | British Standard: BS 680 Part 2