



# CUPA 98

---

*Non-carbonated **slate** formed by tectonic compression.  
Dark **grey** slate with thin laminations and a **riven** surface.*





Quarry Rande, Ortigueira (A Coruña), Spain.



Operating since 1969.



Main sizes: 10"x10" to 24"x12"  
Thickness: 3/16" to 3/8"



## Formats



Rectangular

## Selections

EXCELLENCE

HEAVY

## Technical specifications

ABSORPTION	CARBONATE NON CARBONATED	MOR CHARACTERISTIC	SO <sub>2</sub> EXPOSURE TEST	THERMAL CYCLE TEST	FREEZE THAW TEST
< 0,4% Code : W1 (< 0,6%)	≤ 0,2% Fullfil (< 2%)	Longitudinal ≥ 58 MPA	S1	T1	Fullfil < 0,6%

## International certifications



European Standard: EN 12326 | French Specifications: NF 02/10 - N° 27958 | British Standard: BS 680 Part 2